



PRO-MIX™

ACCELERATED CONCRETE MIX



PRODUCT SPECIFICATIONS*		
SIZE	UPC#	QTY
50 lb bag	7-42786-91455-2	30/pallet

*Product Availability and Pallet Quantities May Vary by Region

Features:

- High strength and fast setting
- 4000 PSI at 3 hours - 6,000 PSI at 28 days
- Formulated for excellent workability and finishing
- 15 minute set time, open for foot traffic in <1 hour
- Meets or exceeds ASTM C387

Uses:

- Concrete repair and construction where speed is critical
- Application thickness over 2"
- Driveways, sidewalks, and more
- Form work, footings, setting posts, and more

Start Your Next Project Today! Visit [SakretePROMIX.com](https://www.sakretepromix.com)